



# PRINTASLEEVE

## NP

Neoprene sleeving is a very flexible, petrol, oil and ozone resistant tubing made from highly elastic extruded Polychloroprene Rubber quality 3490. It is available in 12 different colours and in diameters of 1.2mm – 17mm as standard. Bespoke sizes and wall thicknesses on application and [cutting](#) and [printing](#) as required.

Also known as Chloroprene, neoprene rubber sleeving is ideal for the binding and identification of cable harnesses, braided mains leads into plugs and portable equipment, and as electrical insulation. It has good elastic and mechanical properties and is not corrosive to metal. Neoprene's elastomeric properties mean a high degree of expansion can be achieved during assembly making it easy to apply either as a continuous length or in cut markers.



## Technical Data

- **Operating Temperature** -30°C-+90°C
- **Colours:** Black, White, Blue, Green, Yellow, Orange, Brown, Red, Purple, Grey, Pink, Light Blue, Green / Yellow
- **Sizes:** 1.2mm ? 17mm
- **Packing:** Coils, cut to length, cut sleeves
- **Print:** Yes, text and logos
- **Approvals:** BS 3858 type 1C, UL approved, RoHS compliant
- **Applications / Industries:** General, Commercial, Electrical, Electronics, Industrial, Mechanical, Automotive

Properties	Typical Values	Test Methods
General		
Operating Temperature	-30°C-+90°C	
Short-term peak temperature	110°C	
Physical		
Tensile Strength	6.5MPa	
Ultimate elongation	>500%	
Hardness	Shore A 40±5	
Tear Resistance	10kN/m	
Thermal		
Flammability	non-flammable	VO UL94
Electrical		
Dielectric strength	13kV/mm	4x10??cm

Size (mm)	Nominal wall thickness (mm)
1.2	0.50
1.75	0.50
2.4	0.60
2.5	0.90
3	0.60
4	1.20
5	0.70
7.5	0.80
10	0.90
12	1.20
14	1.30
17	1.30

Printasleeve Ltd is as diligent as possible in compiling and updating the above information. It reflects averages derived from product sample testing, is subject to normal manufacturing and testing tolerances and may be changed without notice. Furthermore aesthetic and textural style differences can result in local variation. For specific or further information concerning our products, their specifications and their utilization please contact us. E & OE

