



## PRINTASHRINK CPF/FR-L

## TECHNICAL DATA

**Printashrink CPF/FR-L** is a flattened 2:1 shrink ratio heatshrink polyolefin organised on ladder-style carriers. It is supplied in the form of printable labels. The tubing is UL approved, fire retardant, has a working temperature of 125°C and is available in a range of colours and sizes up to 50.8mm ID and can be [printed](#) as required.

This flattened 2:1 heatshrink polyolefin tube can be supplied on a number of differently sized and structured ladder-style carriers making it compatible with most printers. It is a UL/CSA approved sleeve with a 125°C working temperature and has a surface and profile perfect for thermal transfer printing. It is available in varying sleeve lengths to suit any print requirement and set up and is used in a number of commercial and industrial applications. We can supply unprinted or pre-printed as required.

- **SHRINK RATIO** 2:1
- **PACKING** Rolls, mini-packs
- **SHRINK TEMPERATURE** +85°C
- **PRINT** Yes, full range of text and logos
- **OPERATING TEMPERATURE** -40°C – +125°C
- **FLAME RETARDANT** Yes
- **COLOURS** Yellow, White, Other colours available upon request
- **SIZES** 2.4 x 13, 19, 25, 38, 50mm – 50.8 x 13, 19, 25, 38, 50mm
- **APPROVALS** SAE AS81531 :1531:1998 4.6.2, MIL-STD-202F 215J, UL224, CSA certified, RoHS compliant
- **APPLICATIONS** /

Properties	Typical Values	
<b>GENERAL</b>		
Operating temperature	-40°C – +125°C	
Medium Shrink temperature	85°C	
Shrink ratio	2:1	
<b>PHYSICAL</b>		
Tensile Strength	10.4Mpa min	GB/T1040
Ultimate elongation	≥ 200%	GB/T1040
Longitudinal change	+/-5%	UL224
<b>HERMAL</b>		
Flammability	Pass	UL224
Heat shock (4hrs)	No dripping, flowing or cracking	ASTM D 2671
Heat ageing (168hrs)	@ 158°C elongation 100%	ASTM D 638
<b>Size (mm)</b>		<b>Supplied diameter (mm)</b>
2.4 x 13, 19, 25, 38, 50	2.4	0.8
3.2 x 13, 19, 25, 38, 50	3.2	1.0
4.8 x 13, 19, 25, 38, 50	4.8	1.6
6.4 x 13, 19, 25, 38, 50	6.4	2.4
9.5 x 13, 19, 25, 38, 50	9.5	3.2
12.7 x 13, 19, 25, 38, 50	12.7	4.8
19.1 x 13, 19, 25, 38, 50	19.1	6.4
25.4 x 13, 19, 25, 38, 50	25.4	8.4
38.1 x 13, 19, 25, 38, 50	38.1	12.7
		18.0
		0.57
		0.61
		0.67
		0.71
		0.77
		0.80
		0.84
		0.86
		0.89
		0.90

Printasleeve Ltd is as diligent as possible in compiling and updating the above information. It reflects averages derived from product sample testing, is subject to normal manufacturing and testing tolerances and may be changed without notice. Furthermore aesthetic and textural style differences can result in local variation. For specific or further information concerning our products, their specifications and their utilisation please contact us.