



## ENDCAPS

**Printashrink endcaps, breakout boots and moulded shapes are made from heatshrinkable materials and are available with or without adhesive lining. They are used for mechanical protection, strain relief and to provide a watertight seal. They are available in many configurations so please contact us for full details.**

Endcaps are widely used to seal power and telecommunication cables, pipes, conduits and other cylindrical objects against moisture ingress, provide environmental and mechanical protection and prevent corrosion. They have an adhesive lining that melts and flows to provide a tight fit when heat is applied, and are often used in underwater, underground and outdoor applications.

Many other heatshrinkable moulded parts are also available with or without adhesive lining. These can be supplied in various materials (semi-rigid modified polyolefin, modified fluoroelastomer, fluid resistant elastomer), low fire hazard material will meet the requirements for most military, marine, mass transit and commercial applications.

Properties	Typical Values	Test Methods
<b>GENERAL</b>		
Operating Temperature	-55°C – +110°C (jacket)	
Shrink temperature	120°C	
<b>PHYSICAL</b>		
Tensile Strength	12MPa min	ASTM D 638
Ultimate elongation	300% min	ASTM D 638
Water absorption	1% max	ISO 62
Hardness	45 Shore D min	ASTM D 2240
<b>THERMAL</b>		
Heat ageing (168hrs)	at 120°C, tensile 10MPa min, elongation 250% min	
<b>ELECTRICAL</b>		
Dielectric strength	12kV/mm min	IEC 273
Volume resistivity	10 <sup>14</sup> Ωcm min	IEC 93
Size (mm)	Supplied diameter (mm)	Shrunk diameter (mm)
10/3 x 35	10.0	3.0
15/4.5 x 45	15.0	4.5
20/6 x 63	20.0	6.0
25/8.5 x 70	25.0	8.5
40/14.5 x 102	40.0	14.5
63/24 x 118	63.0	24.0
75/32 x 133	75.0	32.0
78/38 x 130	78.0	38.0
100/57 x 155	100.0	57.0
106/45 x 164	106.0	45.0
120/57 x 155	120.0	57.0
145/57 x 155	145.0	57.0

Printasleeve Ltd is as diligent as possible in compiling and updating the above information. It reflects averages derived from product sample testing, is subject to normal manufacturing and testing tolerances and may be changed without notice. Furthermore aesthetic and textural style differences can result in local variation. For specific or further information concerning our products, their specifications and their utilisation please contact us.

## TECHNICAL DATA

- **SHRINK TEMPERATURE • SIZES** 120°C
- **OPERATING TEMPERATURE** -55°C – + 110°C
- **COLOURS** Black

• **APPROVALS**  
General Commercial 15/57 x  
Electrical, Electronics,  
Industrial, Mechanical,  
Automotive, Marine