



**Extruded & non-shrink products** 

## **PVC GP**

PVC GP is a general purpose, flexible non-shrink sleeve with an operating temperature of -25°C-+70°C. It is a low cost solution ideal for many commercial applications and is available in a full range of colours and sizes as standard and can be  $\underline{\text{cut}}$  and  $\underline{\text{printed}}$  as required.

This general purpose PVC hose is a low cost flexible jacket with good dielectric properties, chemical and fungal resistance and low water absorption. It is manufactured from premium virgin grade compound and frequently used in wire harnessing for electrical insulation. It is also used for general protection in a great many other applications including scooter/Vespa/motorcycle maintenance and retro/ period lighting. It is supplied with a 0.5mm nominal wall and in a wide range of metric and AWG sizes and colours including green/yellow for earth as standard. Bespoke sizes and colours are available on enquiry.

Properties	Typical Values	
GENERAL		
Operating temperature	25°C – + 70°C	
PHYSICAL		
Tensile strength	15MPa	
THERMAL		
Flammability	Self extinguishing in 30s	
ELECTRIAL		
Dielectric strength	20kV/mm	
Insulation Resistance	101°Ohm/cm	

## **TECHNICAL DATA**

- OPERATING TEMPERATURE -25°C-+70°C
- FLAME RETARDANT
  - Self extinguishing
- COLOURS

Black, Brown, Blue, Green, Yellow, Grey, White, Red, Green / Yellow, (Pink / Violet / Orange available to order)

SIZES

1mm - 25mm

PACKING

Coils, reels, cut to length, cut sleeves

PRINT

Yes, full range of text and logos

APPROVALS

**RoHS Compliant** 

APPLICATIONS / INDUSTRIES

General, Commercial, Electrical, Electronics, Industrial, Mechanical, Automotive

Size (mm)			
1	1.0	0.40	
1.5	1.5	0.40	
2	2.0	0.40	
3	3.0	0.40	0.5 - 0.75
4	4.0	0.40	1.5 – 2.5
5	5.0	0.45	2.5 - 4.0
6	6.0	0.45	6.0
8	8.0	0.45	10.0
10	10	0.45	16.0 – 25.0
12	12.0	0.45	35.0
15	15.0	0.45	50.0
18	18.0	0.45	70.0
20	20.0	0.45	95.0
25	25.0	0.45	

Printasleeve Ltd is as diligent as possible in compiling and updating the above information. It reflects averages derived from product sample testing, is subject to normal manufacturing and testing tolerances and may be changed without notice. Furthermore aesthetic and textural style differences can result in local variation. For specific or further information concerning our products, their specifications and their utiliation please contact us.

