



PVC 105T

PVC 105T is a flexible non-shrink sleeve with an operating temperature of -40°C-+105°C. It conforms to specification BS2848/3/105T and is ideal for applications with higher temperature requirements. It is available in a full range of colours and sizes and can be [cut](#) and [printed](#) as required.

This higher temperature PVC hose with BS accreditation is a low cost flexible jacket with good dielectric properties, chemical and fungal resistance and low water absorption. It is manufactured from premium virgin grade compound and frequently used in wire harnessing for electrical insulation. It is supplied with a 0.5mm nominal wall, in a wide range of metric and AWG sizes and many colours including green/yellow for earth as standard. Bespoke sizes, wall thicknesses and colours are available on enquiry.

TECHNICAL DATA

- **OPERATING TEMPERATURE**
-40°C – + 105°C
- **FLAME RETARDANT**
Self extinguishing
- **COLOURS**
Black, Brown, Blue, Green, Yellow, Grey, White, Red, Green / Yellow, (Pink / Violet / Orange to order)
- **SIZES**
1mm – 25mm
- **PACKING**
Coils, reels, cut to length, cut sleeves
- **PRINT**
Yes, full range of text and logos
- **APPROVALS**
BS 2848/3/85T, RoHS compliant
- **APPLICATIONS / INDUSTRIES**
General, Commercial, Electrical, Electronics, Industrial, Mechanical, Automotive

Properties	Typical Values
GENERAL	
Operating temperature	-40°C – + 105°C
PHYSICAL	
Ultimate elongation	250%
Hardness	BSS25-35
THERMAL	
Flammability	Self extinguishing in 30s
ELECTRIAL	
Dielectric strength	25kV/mm
Insulation Resistance	10 ¹² Ω/cm

Size (mm)	Supplied diameter (mm)	Nominal wall thickness (mm)
1	1	0.5
1.5	1.5	0.5
2	2	0.5
3	3	0.5
4	4	0.5
5	5	0.5
6	6	0.5
8	8	0.5
9	9	0.5
10	10	0.5
12	12	0.5
15	15	0.5
20	20	0.5
25	25	0.5

Printasleeve Ltd is as diligent as possible in compiling and updating the above information. It reflects averages derived from product sample testing, is subject to normal manufacturing and testing tolerances and may be changed without notice. Furthermore aesthetic and textural style differences can result in local variation. For specific or further information concerning our products, their specifications and their utilisation please contact us.